

Dow Corning[®] 799 Silicone Glass and Metal Building Sealant

FEATURES

- Primerless – can be used with many materials without the use of a primer
- Noncorrosive – will not react with or corrode common building materials
- Fast cure – 5 to 10 minutes tooling time and 20 minutes tack-free time
- Excellent weather resistance against sunlight, rain, snow, and temperature extremes
- Long-life reliability – cured sealant stays elastic from -40°C to 149°C (-40 to 300°F)
- AAMA Certified

COMPOSITION

- One-part RTV silicone sealant

Silicone sealant for glazing and weathersealing applications

APPLICATIONS

Dow Corning[®] 799 Silicone Glass and Metal Building Sealant is designed for:

- Conventional glazing applications
- Weatherseal applications including perimeter sealing of doors and windows
- Sealing around metal building flashings, gutters and gutter outlets
- Factory-applied glass where it would serve as the primary seal bedding compound in a finished sash

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test*	Property	Unit	Result
As Supplied			
ASTM C 679	Tack-Free Time, 50% RH	minutes	20
	Curing Time, 50% RH at 25°C(77°F)	days	7 – 14
ASTM D 2202	Flow, Sag or Slump		Nil
	Working Time minutes		5 – 10
As Cured			
ASTM C 661	Durometer Hardness, Shore A	points	30
As Cured – After 14 days at 25°C (77°F)			
ASTM D 412	Ultimate Tensile Strength	psi (MPa)	230 (1.59)
ASTM D 412	Ultimate Elongation	percent	500

*ASTM: American Society for Testing and Materials.

DESCRIPTION

Dow Corning 799 Silicone Glass and Metal Building Sealant is a noncorrosive sealant that cures in the presence of atmospheric moisture. This product exhibits unprimed adhesion to many construction materials. Once cured, the sealant forms a durable and flexible bond with most building materials. In most cases, no prime coat is required.

Dow Corning 799 Silicone Glass and Metal Building Sealant available in clear, black, white and gray.

Dow Corning 799 Silicone Glass and Metal Building Sealant will provide

years of worry-free performance against rain, sun, and temperature extremes.

Approvals/Specifications

ASTM Specification C-920 Type S, Grade NS, Class 25, Use NT, G and A.

HOW TO USE

Please refer to the Dow Corning Americas Technical Manual, Form No. 62-1112, for detailed information on joint design, surface preparation and installation procedures.

Preparation

Clean all joints and glazing pockets, removing all foreign matter and contaminants such as grease, oil, dust, water, frost, surface dirt, old sealants or glazing compounds, and protective coatings.

Metal, glass and plastic surfaces should be cleaned by mechanical or solvent procedures. Detergent or soap and water treatment are not acceptable. In all cases where used, solvents should be wiped on and off with clean, oil-and lint-free cloths.¹

Priming

Consult Dow Corning for priming recommendations for various substrates. NOTE: Prior to general job use, place a bead of sealant on the substrate material to test adhesion.

Application

Install back-up material or joint filler, setting blocks, spacer shims and tapes as specified. Apply *Dow Corning 799 Silicone Glass and Metal Building Sealant* in a continuous operation using a positive pressure adequate to properly fill and seal the joint.

Tool or strike *Dow Corning 799 Silicone Glass and Metal Building Sealant* with light pressure to spread the material against the back-up material and the joint surfaces. A tool with a concave profile is recommended to keep the sealant within the joint.

Dow Corning 799 Silicone Glass and Metal Building Sealant can be applied at outdoor temperatures as low as -37°C (-35°F) provided that surfaces are clean, dry and frost-free.

Excess sealant should be cleaned from glass, metal and plastic surfaces while still uncured using a commercial solvent such as isopropyl, xylene, toluene or methyl ethyl ketone.¹

Use only with adequate ventilation. Avoid prolonged breathing of vapor and prolonged or repeated skin contact. Always follow solvent container label instructions and local, state and federal regulations.

HANDLING PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE AT DOWCORNING.COM, OR FROM YOUR DOW CORNING REPRESENTATIVE, OR DISTRIBUTOR, OR BY CALLING YOUR GLOBAL DOW CORNING CONNECTION.

USABLE LIFE AND STORAGE

When stored in original, unopened containers at or below 32°C (90°F), *Dow Corning 799 Silicone Glass and Metal Building Sealant* has a usable life of 24 months from date of manufacture. Refer to product packaging for "Use By" date.

PACKAGING INFORMATION

Dow Corning 799 Silicone Glass and Metal Building Sealant is packaged in 10.3-fl oz (305-mL) disposable cartridges that fit ordinary caulking guns, 4.5-gal (17-L) bulk pails and 48-gal (182.4-L) fiber drums. It can be dispensed by many air-operated guns and most types of bulk dispensing equipment.

LIMITATIONS

Dow Corning 799 Silicone Glass and Metal Building Sealant is not recommended for use:

- Below grade or in horizontal joints where physical abuse or abrasion is likely to be encountered

- For structural silicone glazing applications
- In totally confined spaces where sealant cannot cure because of a lack of atmospheric moisture
- On surfaces that will be painted (the paint film will not stretch with the extension of the sealant and may crack or peel)
- On wet or frost-laden surfaces
- On substrates that bleed oil or plasticizers

Dow Corning 799 Silicone Glass and Metal Building Sealant:

- May discolor sensitive metals such as copper and brass
- May stress-crack polycarbonate

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

¹Caution: When using flammable solvents, keep away from heat, sparks and open flames.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING
SPECIFICALLY DISCLAIMS
ANY OTHER EXPRESS OR
IMPLIED WARRANTY OF
FITNESS FOR A PARTICULAR
PURPOSE OR
MERCHANTABILITY.
DOW CORNING DISCLAIMS
LIABILITY FOR ANY
INCIDENTAL OR
CONSEQUENTIAL DAMAGES.**

We help you invent the future.™

dowcorning.com