



GREAT STUFF PRO GAPS & CRACKS Foam Sealant

Gun (750 ml) and Straw (750 ml / 500ml)

Description

GREAT STUFF* PRO GAPS AND CRACKS is a moisture-curing one-component polyurethane aerosol foam sealant. It contains an environmentally safe propellant, which complies with the latest EU regulations banning all CFC- and HCFC-propellants.

Typical areas of Application

- Filling holes, gaps, cracks and cavities within various building materials.
- Sealing voids and connection joints between different building materials.
- Reducing and controlling air-leakage in the building envelop and thereby sound transmission as well.
- As an aid to mechanically fixing and insulating door and window frames.
- Air sealing and stabilizing pipe entries through brickwork and other walls and showers.

Typical Product Properties

GREAT STUFF PRO GAPS AND CRACKS adheres to most common building materials including wood, concrete, wall board and plastic, with the exception of smooth surfaced polyethylene, silicone, oil and grease or similar substrates.

GREAT STUFF PRO GAPS AND CRACKS can be used at temperatures from +5°C to +25°C, the optimal processing temperatures being from 18°C to 25°C.

Full foam setting time is 12 hours. Once fully set, the foam can be trimmed, sawn, sanded, painted or plastered over.

The fully set foam is semi-rigid and predominantly close-celled.

It is thermally stable between -30°C and +80°C. It is durable and permanent except when exposed to UV-rays. Foam exposed to UV light should be painted or covered.

The heat insulation values are excellent.

Using the **GREAT STUFF PRO GUN FOAM** will guarantee superior dispensing control and maximum reusability.

Recommended Process Conditions

Prior to applying the foam, surfaces must be firm, clean, and free of dust, grease or loose particles. To speed up the curing process, surfaces can be lightly misted with water prior to applying the foam.

We recommend covering the floor and working surfaces with paper or plastic sheeting to protect against drips. It is advisable to have **GREAT STUFF PRO GUN CLEANER** at hand.

The ideal working temperature for both the environment and the can content is +20°C.

Always wear gloves and protective eyewear when dispensing **GREAT STUFF PRO GAPS AND CRACKS**.

Recommended Process Application

The following instructions must be strictly observed:

Shake the can vigorously for 30 seconds. Screw the threaded end of the straw assembly or the gun onto the valve. Care must be taken not to over tighten the dispensing assembly. During processing, the can must be held inverted with the valve in bottom position. To extrude the foam, pressure has to be carefully applied to the straw or gun trigger. The gun trigger can be adjusted by turning the round knob at the rear of the gun dispenser.

The fresh foam will expand after application, therefore care must be taken not to overfill joints.

Please note: Moisture is needed for an even and rapid curing of the foam. Inadequate moistening or overfilling of joints and cavities may lead to poor cure or unwanted excessive post-expansion of the foam.

In the case of gaps larger than 3 x 3 cm, it is recommended to fill by applying several layers of foam, allowing each to cure.

Fresh foam spills must be removed immediately within the Tack-Free time using GREAT STUFF PRO GUN CLEANER. Once foam is cured, it can be removed mechanically.

When using a gun applicator: During relatively short work stoppages, leave the gun dispenser on the can and screw in proportioning screw completely. When a can becomes empty, immediately screw the gun onto another can. During relatively long stoppages, unscrew the can and clean the gun with GREAT STUFF PRO GUN CLEANER.

Once a gun can has been started, it should be used within four weeks.

When using straw assembly: Once opened, the foam will solidify in the straw or in the valve within 20-60 minutes, depending on ambient conditions. Prepare in advance to carry out all foaming at once.

If aerosol can has become bonded to a straw assembly or gun, do not use force to loosen it, as there is danger of uncontrolled product release.

If product does not flow easily, do not force product out of can.

Handling and Storage

Store and transport cans always in an upright position and in dry conditions.

Storage temperature: 15°C – 25°C

Cans should not be stored in hot areas, such as vehicles in direct sunlight.

Shelf life: 12 months

Packaging

Tinplate cans: 750 ml or 500 ml

Carton: 12 cans each

Typical Physical Properties ⁽¹⁾

	Units	Gun (750 ml)	Straw (750 ml)	Straw (500ml)	Test Method
Free rise density	Kg/m ³	15	18	18	DIN 53420
Density (3 cm gap)	Kg/m ³	20	22	22	DIN 53420
Colour		Light yellow	Light yellow	Light yellow	Visual
Yield	l	45	35	23	DOW internal method
Tack free time	min	10	12	12	DOW internal method
Cut time	min	23	25	25	DOW internal method
Tensile strength	N/cm ²	8	8	8	DIN 53430
Compressive strength	N/cm ²	5	5	5	DIN 53421
Shear strength	N/cm ²	5	5	5	DIN 53427
Dimensional stability	%	≤10	≤10	≤10	DIN 53431

1. Based on test methods mentioned above, all data are given for non-aged foam evaluated @ 23°C, 50 % relative humidity. Yield is lower for aged foam. Special applications must be tested individually. For better results, premoisten the surface before dispensing the foam.

Safety Considerations

Material Safety Data (MSD) sheets are available from The Dow Chemical Company. MSD sheets are provided to help customers satisfy their own handling, safety and disposal needs and those that may be required by locally applicable health and safety regulations. MSD sheets are updated regularly, therefore, please request and review the most current MSD sheet before handling or using any product. These are available from the nearest Dow sales office.

Customer Notice

Dow encourages its customers to review their application of Dow products from the standpoint of human health and environmental quality. To help ensure that Dow products are not used in ways for which they were not intended or tested, Dow personnel will assist in dealing with ecological and products safety. Your Dow representative can arrange the proper contacts.

Contact information :

For more information about PU Consumer & Building products, call The Dow Chemical Company :
<http://www.dow.com/pusystems/index.htm>

NOTICE: The information and data contained herein do not constitute sales specifications. The product properties may be changed without notice. No liability, warranty or guarantee of product performance is created by this document. It is the Buyer's responsibility to determine whether Dow products are appropriate for Buyer's use and to ensure that Buyer's workplace and disposal practices are in compliance with applicable laws and regulations. No freedom from any patents owned by Dow or other industrial or intellectual property rights is granted or to be inferred.

